



CARAMEL QUARTZITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	106	5.5	94.4	80-100%
#8	528	27.4	67.0	65-90%
#16	298	15.4	51.6	40-60%
#30	204	10.6	41.0	25-55%
#50	210	10.9	30.1	15-35%
#100	244	12.6	17.5	10-20%
#200	182	9.4	8.1	7-15%
Pan	156	8.1	0.0	
TOTAL	1928			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	106	5.5	94.4	80-100%
#8	528	27.4	67.0	55-90%
#16	298	15.4	51.6	40-60%
#30	204	10.6	41.0	25-55%
#50	210	10.9	30.1	15-35%
#100	244	12.6	17.5	10-20%
#200	182	9.4	8.1	5-15%
Pan	156	8.1	0.0	
TOTAL	1928			