



CHOCOLATE BROWN GRANITE PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	204	10.2	89.8	80-100%
#8	458	22.9	66.9	65-90%
#16	376	18.8	48.1	40-60%
#30	284	14.2	33.9	25-55%
#50	176	8.8	25.1	15-35%
#100	148	7.4	17.7	10-20%
#200	134	6.7	11.0	7-15%
Pan	220	11.0	0.0	
TOTAL	2000			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	204	10.2	89.8	80-100%
#8	458	22.9	66.9	55-90%
#16	376	18.8	48.1	40-60%
#30	284	14.2	33.9	25-55%
#50	176	8.8	25.1	15-35%
#100	148	7.4	17.7	10-20%
#200	134	6.7	11.0	5-15%
Pan	220	11.0	0.0	
TOTAL	2000			