



COLONIAL RED GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	10	0.6	99.3	80-100%
#8	500	28.4	70.9	65-90%
#16	382	21.7	49.2	40-60%
#30	274	15.6	33.6	25-55%
#50	196	11.1	22.5	15-35%
#100	128	7.3	15.2	10-20%
#200	86	4.9	10.3	7-15%
Pan	182	10.3	0.0	
TOTAL	1758			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	10	0.6	99.3	80-100%
#8	500	28.4	70.9	55-90%
#16	382	21.7	49.2	40-60%
#30	274	15.6	33.6	25-55%
#50	196	11.1	22.5	15-35%
#100	128	7.3	15.2	10-20%
#200	86	4.9	10.3	5-15%
Pan	182	10.3	0.0	
TOTAL	1758			