

## SPECIFICATIONS

A rich black quartzite with a subtle mica fleck in a sophisticated square cut.

### THIN VENEER

LENGTH	4" - 24" Random (12" Average)
HEIGHT	4" - 12" Random
THICKNESS	¾" - 1 ¼"
YIELD	10-15 lbs/ft²

### ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.12%
BULK SPECIFIC GRAVITY	2.782

### ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	19,870 psi
PARALLEL TO RIFT, WET	8,452 psi
PERPENDICULAR TO RIFT, DRY	19,013 psi
PERPENDICULAR TO RIFT, WET	8,088 psi

### ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	2,086 psi
PARALLEL TO RIFT, WET	1,173 psi
PERPENDICULAR TO RIFT, DRY	1,584 psi
PERPENDICULAR TO RIFT, WET	1,142 psi

### ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	1,341 psi
PARALLEL TO RIFT, WET	1,053 psi
PERPENDICULAR TO RIFT, DRY	1,883 psi
PERPENDICULAR TO RIFT, WET	1,395 psi

