

SPECIFICATIONS

A rich black quartzite with a subtle mica fleck, mixed with occasional gray seam face stone in a casual, irregular look.

THIN VENEER

| | |
|-----------|--------------------|
| LENGTH | 6" - 16" Irregular |
| HEIGHT* | 6" - 16" Irregular |
| THICKNESS | ¾" - 1 ½" |
| YIELD | 10-15 lbs/ft² |

ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

| | |
|-----------------------|-------|
| WATER ABSORPTION | .12% |
| BULK SPECIFIC GRAVITY | 2.782 |

ASTM C-170 – COMPRESSIVE STRENGTH

| | |
|----------------------------|------------|
| PARALLEL TO RIFT DRY | 19,870 psi |
| PARALLEL TO RIFT, WET | 8,452 psi |
| PERPENDICULAR TO RIFT, DRY | 19,013 psi |
| PERPENDICULAR TO RIFT, WET | 8,088 psi |

ASTM C-99 – MODULUS OF RUPTURE

| | |
|----------------------------|-----------|
| PARALLEL TO RIFT DRY | 2,086 psi |
| PARALLEL TO RIFT, WET | 1,173 psi |
| PERPENDICULAR TO RIFT, DRY | 1,584 psi |
| PERPENDICULAR TO RIFT, WET | 1,142 psi |

ASTM C-880 – FLEXURAL STRENGTH

| | |
|----------------------------|-----------|
| PARALLEL TO RIFT DRY | 1,341 psi |
| PARALLEL TO RIFT, WET | 1,053 psi |
| PERPENDICULAR TO RIFT, DRY | 1,883 psi |
| PERPENDICULAR TO RIFT, WET | 1,395 psi |

