GUN METAL MARBLE DIMENSIONAL

SPECIFICATIONS

A modern cool-toned blue-gray natural stone accented by warm buff tones.

	THIN VENEER
LENGTH	4" - 30" Random (10" Average)
HEIGHT*	Sawn 2 ¼", 5", & 7 ¾"
THICKNESS	³ /4" - 1 ¹ /2"
YIELD *Typical height ratio: 20% = 2 ¼ ² , 50% = 5 ⁷	10 - 15 lbs/ft² . 30% = 7 %. Additional heights available upon request

ASTM C-97 - ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.03%
BULK SPECIFIC GRAVITY	2.823

ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	22,500 psi
PARALLEL TO RIFT, WET	24,370 psi
PERPENDICULAR TO RIFT, DRY	31,720 psi
PERPENDICULAR TO RIFT, WET	30,430 psi

ASTM C-99 - MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	1,040 psi
PARALLEL TO RIFT, WET	1,600 psi
PERPENDICULAR TO RIFT, DRY	1,660 psi
PERPENDICULAR TO RIFT, WET	1,450 psi

ASTM C-880 - FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	2,160 psi
PARALLEL TO RIFT, WET	1,560 psi
PERPENDICULAR TO RIFT, DRY	3,830 psi
PERPENDICULAR TO RIFT, WET	3,000 psi



